

- [54] METHOD FOR IMPROVING THE CRIMPING OF POLYOLEFIN FILTER TOW
- [75] Inventors: Michael Hill, Ascot, England;
Walter A. Nichols, Richmond, Va.
- [73] Assignee: Filter Materials Limited, New York, N.Y.
- [21] Appl. No.: 231,148
- [22] Filed: Aug. 10, 1988
- [51] Int. Cl.³ D01D 5/22; D01D 5/42
- [52] U.S. Cl. 264/25; 264/26;
264/147; 264/168; 264/563; 264/DIG. 47
- [58] Field of Search 264/DIG. 47, 563, 25,
264/26, 147, 168; 28/257

3,726,079	4/1973	Feild et al.	57/155
3,739,053	6/1973	Yazawa	264/154
3,756,484	9/1973	Guenther	225/97
3,787,261	1/1974	Heger et al.	156/84
3,801,252	4/1974	Waterhouse	425/304
3,835,513	9/1974	Stanley	28/72.14
3,880,173	4/1975	Hill	131/269
3,883,936	5/1975	Stanley	28/72.14
3,927,957	12/1975	Chill et al.	425/131.1
3,949,454	4/1976	Irwin	28/72.14
3,985,600	10/1976	Blais	156/229
3,985,933	10/1976	Mehita et al.	428/357
4,129,632	12/1978	Olson et al.	264/40.1
4,133,087	1/1979	Li	28/257
4,133,088	1/1979	Hikobe	264/DIG. 47
4,134,951	1/1979	Dow et al.	264/147
4,273,600	6/1981	Luke	156/180

[56] References Cited

U.S. PATENT DOCUMENTS

2,914,810	12/1959	Robinson et al.	19/66
3,336,174	8/1967	Dyer et al.	264/DIG. 47
3,398,441	8/1986	Adachi et al.	264/DIG. 47
3,494,522	2/1970	Kim et al.	225/97
3,495,752	2/1970	Kim et al.	225/3
3,496,260	2/1970	Guenther et al.	264/156
3,500,517	3/1970	Dekker et al.	28/1.5
3,500,518	3/1970	Stanley et al.	28/1.6
3,500,627	3/1970	Kim	57/140
3,526,349	9/1970	Moro	225/97
3,565,308	2/1971	Slack	225/97
3,566,735	3/1971	Greene	83/344
3,577,724	5/1971	Greene	57/157
3,579,618	5/1971	Stewart et al.	264/DIG. 47
3,582,418	6/1971	Schuur	264/DIG. 47
3,593,454	7/1971	Kalwaites	225/3

FOREIGN PATENT DOCUMENTS


971878	10/1964	United Kingdom
1207733	10/1970	United Kingdom
1260957	1/1972	United Kingdom
1339496	12/1973	United Kingdom

Primary Examiner—James Lowe
Attorney, Agent, or Firm—Jeffrey H. Ingerman

[57] ABSTRACT

A method is provided for heating fibrillated polyolefin film prior to crimping, to improve the crimping, and thus the yield and variability as a filter, of the tow. The fibrillated tow is crimped while still hot from the heating step. The resulting fibers have more uniform crimping at higher levels than those not subject to heating.

19 Claims, 2 Drawing Sheets



2021343045